

# ***WATER SPORTS***





## LUPES® WAX

### APPLICATIONS

PARASAILING LINE


### SPECIFICATIONS

MATERIAL	COVER : HT WAXED POLYESTER FIBER CORE : HT POLYESTER FIBER
SPECIFIC GRAVITY	1,38 KG/DM <sup>3</sup>
CONSTRUCTION	COVER : 16-24 PLAITED, CORE : 12-16 PLAITED
UV RESISTANCE	EXCELLENT
CHEMICAL RESISTANCE	GOOD
MELTING POINT	256°C
CRITICAL TEMPERATURE	170°C
WORKING STRETCH	<4%
FIBER WATER ABSORPTION	APPROX. %1-2
WET ABRASION	EXCELLENT
LENGTH	100-200 M ORANGE SPOOL OR COIL

OTHER COLOURS & LARGER DIAMETERS UPON REQUEST

ART.NO	DIA	WEIGHT	B.LOAD
	(Ø)	(kg / 100 m)	(kgf)*
020	8	5,50	1.550
020	9	7,50	2.000
020	10	8,75	2.330
020	11	11,00	2.800
020	12	12,50	3.270

\*UNSPliced BREAK LOAD (ALL TESTS ARE IN ACCORDANCE WITH ISO 2307)



### BENEFITS / FEATURES

- OUTSTANDING FLEXIBILITY
- HIGH BREAKING LOAD
- EASY TO SPLICE



## DYNEEMA®

### APPLICATIONS

PARASAILING LINE

### SPECIFICATIONS

MATERIAL	COATED DYNEEMA® SK 78/99
SPECIFIC GRAVITY	0,97 KG/DM <sup>3</sup>
CONSTRUCTION	12 STRAND BRAIDED
UV RESISTANCE	EXCELLENT
CHEMICAL RESISTANCE	EXCELLENT
MELTING POINT	147°C
CRITICAL TEMPERATURE	65°C
WORKING STRETCH	<1%
FIBER WATER ABSORPTION	NONE
WET ABRASION	EXCELLENT
DRY ABRASION	EXCELLENT
LENGTH	100-200 M ORANGE SPOOL OR COIL

OTHER COLOURS & LARGER DIAMETERS UPON REQUEST

ART.NO	DIA (Ø)	WEIGHT (kg / 100 m)	B.LOAD (kgf)*	
			SK78 (ART.NO: 005)	SK99 (ART.NO: 505)
005 - 505	6	2,30	3.750	4.425
005 - 505	8	4,00	6.600	7.788
005 - 505	10	6,10	10.400	12.272
005 - 505	12	8,70	16.600	17.700

\*UNSPliced BREAK LOAD (ALL TESTS ARE IN ACCORDANCE WITH ISO 2307)



### BENEFITS / FEATURES

- EXCELLENT BREAKING LOAD (SK99)
- BUOYANT
- DURABLE
- VERY LOW STRETCH
- LIGHTWEIGHT
- EASY TO SPLICE
- DOES NOT KINK

OVERPOWER



BENEFITS / FEATURES
EXCELLENT DURABILITY
LOW STRETCH
HIGH STRENGTH

APPLICATIONS

WINDSURF OUTHAULS / DOWNHAULS

SPECIFICATIONS

MATERIAL	COATED DYNEEMA® SK 78
SPECIFIC GRAVITY	0,97 KG/DM <sup>3</sup>
CONSTRUCTION	12 STRAND BRAIDED
UV RESISTANCE	EXCELLENT
CHEMICAL RESISTANCE	EXCELLENT
MELTING POINT	147°C
CRITICAL TEMPERATURE	65°C
WORKING STRETCH	<2%
FIBER WATER ABSORPTION	NONE
WET ABRASION	EXCELLENT
DRY ABRASION	EXCELLENT
LENGTH	100-200 M ORANGE SPOOL OR COIL

OTHER COLOURS & LARGER DIAMETERS UPON REQUEST

ART.NO	DIA (Ø)	WEIGHT (kg / 100 m)	B.LOAD (kgf)*
905	4	0,85	650

\*UNSPliced BREAK LOAD (ALL TESTS ARE IN ACCORDANCE WITH ISO 2307)



